

# Generic TES

Styrenic Thermoplastic Elastomer

Generic

## Message:

This data represents typical values that have been calculated from all products classified as: Generic TES

This information is provided for comparative purposes only.

| General Information          |               |                   |             |
|------------------------------|---------------|-------------------|-------------|
| Physical                     | Nominal Value | Unit              | Test Method |
| Density (23°C)               | 0.898 to 1.20 | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage (23°C)     | 0.10 to 4.7   | %                 | ISO 294-4   |
| Hardness                     | Nominal Value | Unit              | Test Method |
| Durometer Hardness (23°C)    | 33 to 88      |                   | ASTM D2240  |
| Mechanical                   | Nominal Value | Unit              | Test Method |
| Tensile Stress (Break, 23°C) | 2.10 to 10.2  | MPa               | ISO 527-2   |
| Tensile Strain (Break, 23°C) | 360 to 710    | %                 | ISO 527-2   |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

