

UBE Polyethylene J3519

Polyethylene
UBE America, Inc.

Message:
UBE Polyethylene J3519 is a Polyethylene material. It is available in North America for injection molding.

General Information			
Features	Good Flow		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.916	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR)	35	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	44		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	8.50	MPa	ASTM D638
Tensile Elongation (Break)	300	%	ASTM D638
Apparent Bending Modulus	100	MPa	ASTM D747
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-40.0	°C	ASTM D746
Vicat Softening Temperature	77.0	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT