

OmniPro™ TPO MF20 HF HSV

Compounded Polypropylene

OMNI Plastics, LLC

Message:

High Impact Resistant, High Stiffness, Mineral Reinforced, Heat & UV Stabilized Thermoplastic Polyolefin

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Additive	Heat Stabilizer		
	UV Stabilizer		
Features	Good UV Resistance		
	Heat Stabilized		
	High Impact Resistance		
	High Stiffness		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	59		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	18.6	MPa	ASTM D638
Flexural Modulus	1900	MPa	ASTM D790
Flexural Strength	22.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.18 mm	110	J/m	
23°C, 3.18 mm	No Break		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.18 mm)	104	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		Internal Method
Injection	Nominal Value	Unit	
Rear Temperature	204 to 249	°C	
Middle Temperature	216 to 260	°C	
Front Temperature	216 to 260	°C	
Nozzle Temperature	216 to 260	°C	

Processing (Melt) Temp	216 to 260	°C
Mold Temperature	26.7 to 60.0	°C
Back Pressure	0.345 to 0.689	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

