

Miflon® 2111B

Polytetrafluoroethylene

Jiangsu Meilan Chemical Co., Ltd.

Message:

Dispersion PTFE Resin (PTFE)

Quality Standard: Q/321200GDH009-2011

Reference Standard: HG/T3028-1999

| General Information | | |
|----------------------------|---------------|-------------------|
| Appearance | White | |
| Forms | Dispersion | |
| Physical | Nominal Value | Unit |
| Specific Gravity | 2.16 to 2.24 | g/cm ³ |
| Apparent Density | 0.38 to 0.58 | g/cm ³ |
| Average Particle Size | 400 to 700 | μm |
| Moisture Content | < 0.040 | % |
| Mechanical | Nominal Value | Unit |
| Tensile Strength | > 32.0 | MPa |
| Tensile Elongation (Break) | > 300 | % |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT