FLEXAREN® 09009

Ethylene Vinyl Acetate Copolymer

Innospec Leuna GmbH

Message:

FLEXAREN® 09009 - high quality ethylene vinyl acetate copolymer with 9% content of vinyl acetate. Manufactured by high pressure tubular process FLEXAREN® 09009 is more elastic than LDPE and compatible with a wide range of polymers. It can be processed with the same equipment.

| General Information | | | |
|---------------------------------------|-----------------------------|----------|---------------|
| Features | Copolymer | | |
| | Good Flexibility | | |
| | Low Temperature Flexibility | | |
| | | | |
| Uses | Masterbatch | | |
| | Sealants | | |
| | | | |
| Appearance | Natural Color | | |
| Forms | Granules | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density (20°C) | 0.926 | g/cm³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 | | | |
| kg) | 9.0 | g/10 min | ISO 1133 |
| Vinyl Acetate Content | 9.0 | wt% | |
| Hardness | Nominal Value | Unit | Test Method |
| Shore Hardness | | | ISO 868 |
| Shore A | 94 | | |
| Shore D | 40 | | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress | | | ISO 527-2/1BA |
| Break | 13.0 | MPa | |
| 50% Strain | 5.90 | MPa | |
| Tensile Strain (Break) | > 700 | % | ISO 527-2/1BA |
| Thermal | Nominal Value | Unit | Test Method |
| Vicat Softening Temperature | 70.0 | °C | ISO 306/A |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 100 to 150 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

