

LNP™ THERMOCOMP™ 9X99089 compound

Polyether Imide

SABIC Innovative Plastics Europe

Message:

LNP THERMOCOMP 9X99089 is a compound based on Polyetherimide resin containing Carbon Fiber. Added features include : Electrically Conductive.

General Information			
Filler / Reinforcement	Carbon Fiber		
Features	Electrically Conductive		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.34	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.040	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11100	MPa	ISO 527-2/1
Tensile Stress (Break)	185	MPa	ISO 527-2/5
Tensile Strain (Break)	1.7	%	ISO 527-2/5
Flexural Modulus ¹	10900	MPa	ISO 178
Flexural Stress	214	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	6.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	40	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed, 64.0 mm Span)	213	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	343 to 354	°C	
Middle Temperature	354 to 366	°C	
Front Temperature	366 to 377	°C	
Processing (Melt) Temp	360 to 366	°C	
Mold Temperature	121 to 149	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	60 to 100	rpm	
NOTE			
1.	2.0 mm/min		
2.	80*10*4		

3.	80*10*4
4.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

