

Luran® 348Q

Styrene Acrylonitrile
Styrolution

Message:

Luran 348Q is an easy-flow grade of SAN, suitable for moldings with very thin walls and / or adverse flow length to wall ratio. It features excellent transparency and a light intrinsic color.

General Information			
UL YellowCard	E108538-100840246		
Features	Good Chemical Resistance		
	Good Flow		
	Good Surface Finish		
	High Clarity		
Uses	Cosmetic Packaging		
	Thin-walled Parts		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	19.0	cm ³ /10min	ISO 1133
Molding Shrinkage	0.30 to 0.70	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	77		
Ball Indentation Hardness	160	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3600	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	70.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.5	%	ISO 527-2
Flexural Stress	115	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	1.5	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	14	kJ/m ²	ISO 179
Notched Izod Impact Strength (23°C)	1.5	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			

0.45 MPa, Annealed	99.0	°C	ISO 75-2/B
1.8 MPa, Annealed	86.0	°C	ISO 75-2/A
Vicat Softening Temperature	105	°C	ISO 306/B50
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.17	W/m/K	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Dielectric Constant (100 Hz)	2.90		IEC 60250
Dissipation Factor			IEC 60250
100 Hz	4.0E-3		
1 MHz	7.0E-3		
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.569		ISO 489
Transmittance (550 nm)	> 89.0	%	ASTM D1003
Haze	< 1.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	200 to 250	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

