

EnviroNylon N6633HSL

Polyamide 66

West Michigan Compounding

Message:

EnviroNylon N6633HSL is a Polyamide 66 (Nylon 66) product filled with 33% glass fiber. It can be processed by injection molding and is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Features	General Purpose		
Uses	General Purpose		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Ash Content	33	%	ASTM D5630
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	162	MPa	ASTM D638
Flexural Modulus	9310	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1100	J/m	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

