

TAROMID B 240

Polyamide 6

Taro Plast S.p.A.

Message:

Polyamide 6 low viscosity.
Available: all colors also dry blend (DB), UV stabilized (L), heat stabilized (H), fast cycles (S) and lubricated (W).

General Information			
Additive	Heat Stabilizer		
	Lubricant		
	UV Stabilizer		
Features	Fast Molding Cycle		
	Good UV Resistance		
	Heat Stabilized		
	Low Viscosity		
	Lubricated		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13 to 1.14	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/1.0 kg)	25	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			ASTM D955
Flow	1.1 to 1.6	%	
Across Flow	1.1 to 1.6	%	
Water Absorption			
23°C, 24 hr	2.0	%	ASTM D570, ISO 62
Saturation	9.0	%	ASTM D570
Saturation, 23°C	9.0	%	ISO 62
Granule Humidity	< 0.10	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2850	MPa	ASTM D638, ISO 527-2
Tensile Strength			ASTM D638, ISO 527-2
Yield	70.0	MPa	
Break	62.0	MPa	
Tensile Elongation (Break)	100	%	ASTM D638, ISO 527-2

Flexural Modulus	2750	MPa	ASTM D790, ISO 178
Flexural Stress			
--	105	MPa	ISO 178
Yield	105	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹ (23°C)	3.0	kJ/m ²	ASTM D256, ISO 179
Notched Izod Impact (23°C, 3.20 mm)	40	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	74.0	°C	ASTM D648, ISO 75-2/A
Continuous Use Temperature ²	80.0	°C	IEC 60216
Vicat Softening Temperature			
--	210	°C	ASTM D1525, ISO 306/A50 ³
--	200	°C	ASTM D1525, ISO 306/B50 ⁵
Ball Pressure Test (165°C)	Pass		VDE 0470
Melting Temperature	220	°C	ASTM D211, ISO 121
CLTE - Flow (-30 to 30°C)	7.0E-5 to 8.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	5.0E+15	ohms·cm	ASTM D257
Dielectric Strength (2.00 mm)	18	kV/mm	ASTM D149
Comparative Tracking Index (Solution A)	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.970 mm)	V-2		UL 94
Glow Wire Ignition Temperature (2.00 mm)	750	°C	IEC 60695-2-13
Oxygen Index	23	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature			
--	80.0 to 90.0	°C	
Pre-heater	80.0 to 100	°C	
Drying Time			
--	1.0	hr	
Pre-heater	3.0	hr	
Processing (Melt) Temp	220 to 240	°C	
Mold Temperature	70.0 to 80.0	°C	
Injection Rate	Moderate		
NOTE			
1.	6x4x50 mm		
2.	20000 hrs		
3.	Rate A (50°C/h), Loading 1 (10 N)		
4.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

