

Generic TEEE - Glass Fiber

Thermoplastic Elastomer, Ether-Ester

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic TEEE - Glass Fiber
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22 - 1.47	g/cm ³	ASTM D792
Molding Shrinkage - Flow (23°C)	0.10 - 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	414 - 3310	MPa	ASTM D638
Tensile Strength (23°C)	42.4 - 43.4	MPa	ASTM D638
Tensile Elongation (Yield, 23°C)	7.3 - 20	%	ASTM D638
Flexural Modulus (23°C)	345 - 2550	MPa	ASTM D790
Flexural Strength (23°C)	12.1 - 75.8	MPa	ASTM D790
Injection	Nominal Value	Unit	
Drying Temperature	104 - 105	°C	
Processing (Melt) Temp	224	°C	
Injection instructions			

This data represents typical values that have been calculated from all products classified as: Generic TEEE - Glass FiberThis information is provided for comparative purposes only.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT