

POCAN® BFN 4211 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, 13 % glass fibers, injection molding, halogen free flame retardant

General Information			
Filler / Reinforcement	Glass Fiber,13% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.43	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	15.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Across Flow : 260°C, 2.00 mm ¹	1.1	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.10	%	
Flow : 260°C, 2.00 mm ³	0.60	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	6200	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	75.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.7	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	6700	MPa	ISO 178/A
Flexural Stress ⁶ (23°C)	125	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	2.7	%	ISO 178/A
ISO Shortname	PBT, GFHMR, 09-060, GF13; ISO 1043-PBT GF FR (30+40)		ISO 7792
Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	25	kJ/m ²	
23°C	30	kJ/m ²	
Notched Izod Impact Strength (23°C)	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	23	kJ/m ²	
23°C	25	kJ/m ²	

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	190	°C	ISO 75-2/A
Vicat Softening Temperature	206	°C	ISO 306/B50
Ball Pressure Test (215°C)	Pass		IEC 60695-10-2
Melting Temperature ⁸	220	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	4.0E-5	cm/cm/°C	
Transverse : 23 to 55°C	9.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	6.6E+15	ohms · cm	IEC 60093
Electric Strength (23°C, 1.00 mm)	33	kV/mm	IEC 60243-1
Comparative Tracking Index (CTI)	PLC 0		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.400 mm	V-0		
0.750 mm	V-0		
	V-0		
1.50 mm	5VA		
	V-0		
3.00 mm	5VA		
Glow Wire Flammability Index			IEC 60695-2-12
0.400 mm	960	°C	
0.750 mm	960	°C	
1.50 mm	960	°C	
3.00 mm	960	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.400 mm	775	°C	
0.750 mm	775	°C	
1.50 mm	775	°C	
3.00 mm	775	°C	
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	70.0 to 90.0	°C	

NOTE	
1.	60x60x2mm, 80°C MT, 600 bar
2.	60x60x2mm
3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

