Silopren® LSR 2060

Silicone Rubber, LSR

Momentive Performance Materials Inc.

Message:

Silopren LSR 2060 is a standard two-component liquid silicone rubber for injection molding processes. Because of its excellent processing properties it can be considered for use in a wide range of applications.

Key Features and Benefits

Vulcanizates consisting of Silopren LSR 2060 typically are distinguished by the following properties:

High thermal stability

Excellent stability and flexibility at low temperatures

Excellent biocompatibility

Sterilizable with ethylene oxide, steam and gamma radiation

Good rubber-like properties

Long service life at dynamic stress

High stability to ozone and ultraviolet light

Outstanding resistance to aging

Excellent dielectric behavior over a wide range of temperatures

Not readily combustible, does not melt or drip

Easily-pigmentable with LSR Color Pastes

Potential Applications

Because of its outstanding properties, Silopren LSR 2060 is an excellent candidate to consider for use in the following elastomeric articles:

Sealing elements

O-rings

Stoppers

Diaphragms

Keypads

Bellows Catheters

Respiratory devices

Diving masks

Vibration dampers

Air vent flaps

Spark plug boots

Switch covers

Pressure cooker parts

Cable connectors

... and many more.

General Information

Features Biocompatible

Ethylene Oxide Sterilizable

Good Colorability

Good Processability

Good Stability

Good Thermal Stability

Good UV Resistance

Low Temperature Flexibility

Ozone Resistant

Radiation Sterilizable

Steam Sterilizable

Vibration Damping

Uses	Connectors			
	Diaphragms			
	Seals			
Agency Ratings	BfR Food Contact, Unspecified Rating			
	DVGW W270			
	FDA 21 CFR 177.2600			
	ISO 10993			
	KTW Unspecified Rating			
	USP Class VI			
	WRAS Unspecified Rating			
UL File Number	E205753			
Forms	Liquid			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	1.13	g/cm³	DIN 53479	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	60		DIN 53505	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Strength	10.0	MPa	DIN 53504	
Tensile Elongation (Break)	450	%	DIN 53504	
Tear Strength ¹	30.0	kN/m	ASTM D624	
Compression Set (175°C, 22 hr)	25	%	ISO 815	
Flammability	Nominal Value Test Method			
Flame Rating	НВ		UL 94	
Thermoset	Nominal Value	Unit	Test Method	
Thermoset Components				
Part A	Mix Ratio by Weight: 1.0			
Part B	Mix Ratio by Weight: 1.0			
Post Cure Time (200°C)	4.0	hr		
Additional Information	Nominal Value	Unit	Test Method	
Vulcanization (175°C)	10.0	min		
Uncured Properties	Nominal Value	Unit	Test Method	
Color				
2	Translucent			
3	Translucent			
Viscosity			DIN 53019	
20°C ⁴	600	Pa∙s		
20°C ⁵	600	Pa·s		
Pot Life (20°C)	4300	min		

NOTE		
1.	Die B	
2.	Part B	
3.	Part A	
4.	Part B	
5.	Part A	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 3