

Epoxies, Ect. 20-2180

Polyurethane
Epoxies, Etc.

Message:

This series of polyurethane systems is engineered for electronic potting, encapsulating, and casting applications. They are low in viscosity, low in toxicity and available in the popular TriggerBond® dual barrel cartridge dispensing system. These elastomeric systems are suitable for a variety of electronic insulating applications. The durometers range from an enterable gel to Shore A 80.

Green:
The base Natural Oil Polyol (NOP) used in these systems is obtained directly from a plant source without chemical modifications. Using renewable resources, such as NOP's, will reduce the demand on non-renewable fossil fuels and reduce the overall production of carbon dioxide.

- Features:
- Green
 - Low Viscosity
 - Available in TriggerBond®
 - Low Durometer
 - Moisture Resistant
 - Convenient Mix Ratios
 - Low Shrinkage & Exotherm
- Benefits
- Reduce demand on non-renewable fossil fuels
 - Quick self leveling around components
 - Easy to use packaging
 - Low stress on components & vibration resistant
 - Can be used in wet environments
 - Easy to process by hand or with meter mix
 - Less stress to components during cure

General Information		
Features	Electrically Insulating	
	Low Exotherm	
	Low Shrinkage	
	Low to No Water Absorption	
	Low Toxicity	
	Low Viscosity	
	Renewable Resource Content	
Uses	Electrical/Electronic Applications	
Appearance	Black	
Processing Method	Casting	
	Encapsulating	
	Potting	
Thermal	Nominal Value	Unit
CLTE - Flow	2.1E-4	cm/cm/°C
Thermal Conductivity	0.30	W/m/K
Electrical	Nominal Value	Unit
Surface Resistivity	> 1.0E+15	ohms

Thermoset	Nominal Value	Unit
Thermoset Mix Viscosity (25°C)	1700	cP
Additional Information	Nominal Value	Unit
Operating Temperature	-30.0 to 125	°C
Uncured Properties	Nominal Value	Unit
Color	Black	
Mix Ratio by Weight (PBW)		
Part A	100	
Part B	60	
Mix Ratio by Volume (PBV)		
Part A	2.0	
Part B	1.0	
Density		
25°C ¹	0.968	g/cm ³
25°C ²	1.15	g/cm ³
Viscosity		
25°C ³	1.5	Pa·s
25°C ⁴	2.2	Pa·s
Curing Time		
85°C	0.66	hr
65°C	1.5	hr
45°C	2.5	hr
25°C	24	hr
Gel Time (25°C)	20	min
Cured Properties	Nominal Value	Unit
Shore Hardness (Shore A)	80	
Tensile Strength	11.7	MPa
Tensile Elongation at Break	220	%
Tear Strength	14.0	kN/m
Electric Strength	26	kV/mm
Relative Permittivity (1 kHz)	3.40	
Volume Resistivity	7.2E+14	ohms·cm
Dissipation Factor (1 kHz)	0.017	
NOTE		
1.	Part B	
2.	Part A	
3.	Part A	
4.	Part B	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

