

Bayflex® XGT-80 (15% Glass)

Polyurethane (Polyether, MDI)

Covestro - PUR

Message:

Bayflex XGT-80 is an elastomeric polyurethane system used in the reaction injection molding (RIM) process. The system is supplied as two liquid components: Component A is a modified diphenylmethane diisocyanate (MDI), and Component B is a polyether polyol system. Note: The polyol component phase-separates upon standing and must be thoroughly mixed via mechanical means prior to use.

The extended gel time of Bayflex XGT-80 gives equipment designers the flexibility to create large, complex parts that can be molded on existing injection machinery. The resin's excellent surface quality and high impact resistance make it a candidate for agricultural equipment, heavy-duty trucks, specialty transportation, and marine applications.

General Information			
Features	Impact resistance, high		
	Excellent appearance		
Uses	Ship application		
	Agricultural application		
Forms	Liquid		
Processing Method	Reaction Injection Molding (RIM)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792, ASTM D1622
Molding Shrinkage - Flow (3.18 mm)	0.55 - 0.65	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 3.18 mm)	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 3.18 mm)	26.2	MPa	ASTM D638
Tensile Elongation (Break, 3.18 mm)	75	%	ASTM D638
Flexural Modulus			ASTM D790
-30°C, 3.18 mm	1930	MPa	ASTM D790
23°C, 3.18 mm	1170	MPa	ASTM D790
70°C, 3.18 mm	538	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ¹ (3.18 mm)	114	kN/m	ASTM D624
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	270	J/m	ASTM D256
Instrumented Dart Impact ²			ASTM D3763
-30°C, 3.18 mm	2.71	J	ASTM D3763
23°C, 3.18 mm	7.73	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow (3.18 mm)	5.6E-5	cm/cm/°C	ASTM D696
Thermoset	Nominal Value	Unit	Test Method

Thermoset Components ³			
Component a	Mixing ratio by weight: 140, mixing ratio by capacity: 120		
Component B	Mixing ratio by weight: 100, mixing ratio by capacity: 100		
Shelf Life ⁴ (32°C)	26	wk	
Demold Time	1.5	min	
Additional Information	Nominal Value	Unit	Test Method
Heat Sag - 4 in Overhang ⁵ (121°C, 3.18 mm)	9.91	mm	ASTM D3769
Part A Type: Isocyanate Appearance: Colorless to straw yellow liquid Specific Gravity @ 25°C: 1.21 Viscosity @25°C: 700 mPa-s Flash Point PMCC: 213 °C NCO: 22.6 - 23.1 % Part B Type: Polyol Appearance: Pale green to amber liquid Specific Gravity @ 25°C: 1.04 Viscosity @25°C: 550 mPa-s Flash Point PMCC: 112 °C Water: <0.09 wt% Molding Parameters Material Temperature - Component A: 32 to 38 °C Material Temperature - Component B: 43 to 49 °C Mold Temperature: 66 to 71 °C Polyol Nucleation - Specific Gravity: 0.9 0 shot time: 10 sec			

NOTE	
1.	C mould
2.	2.24 m/sec
3.	1.05 Index
4.	0.125 in
5.	1 hr

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT