HIPOLEN P® FL 71

Polypropylene Homopolymer

HIPOL A.D.

Message:

HIPOLEN P®FL 71 is a polypropylene homopolymer (PP Homopoly) product. It is available in Africa and the Middle East or Europe. HIPOLEN P®The application areas of FL 71 include film and coating applications. Features include: Antiblock software high gloss slide soft

General Information			
Additive	Anti-caking agent		
	slip agent		
Features	Highlight		
	smoothness		
	Anti-caking property		
	ductility		
Uses	Bi-axially Oriented Film		
	Films		
	Laminate		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/1.2 kg)	1.8	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Elongation (Break)	34	%	ASTM D638
Flexural Modulus	1300	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	50	J/m	ASTM D256
Additional Information			
Thermo Stability, 150°C: 250 hrs			

Thermo Stability, 150°C: 250 hrs

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

