## Epoxies, Ect. 40-3905

Epoxy; Epoxide

Epoxies, Etc.

## Message:

40-3905 is an electrically conductive epoxy system designed for applications requiring low temperature cures. 40-3905 will cure at room temperature in 18-24 hours or can be accelerated with mild heat.

This is a solvent free epoxy system filled with pure silver. It has outstanding adhesion to plastics, aluminum, copper, magnesium, steel, bronze, nickel, kovar, ceramic, glass, phenolic, and printed circuit boards. 40-3905 can also be thinned with up to 10% Toluol for many coating applications.

Features:

Electrically conductive

Thermally conductive

Room temperature cure

Good bond strength

General Information

Filler / Reinforcement	Silver		
Features	Bondability Electrically Conductive Good Adhesion		
Uses	Coating Applications		
	Electrical/Electronic Applications		
	Printed Circuit Boards		
Physical	Nominal Value	Unit	
Molding Shrinkage - Flow	0.30	%	
Mechanical	Nominal Value	Unit	
Flexural Strength	75.2	MPa	
Thermal	Nominal Value	Unit	
CLTE - Flow	2.6E-5	cm/cm/°C	
Thermal Conductivity	8.7	W/m/K	
Additional Information	Nominal Value	Unit	
Operating Temperature	-60.0 to 135	°C	
Uncured Properties	Nominal Value	Unit	
Mix Ratio by Weight (PBW)			
Part A	100		
Part B	5.0		
Density			
25°C <sup>1</sup>	0.998	g/cm³	
25°C <sup>2</sup>	2.97	g/cm³	
Curing Time			
65°C	2.0 to 3.0	hr	

25°C	18 to 24	hr
Pot Life <sup>3</sup> (25°C)	45	min
Shelf Life	12	month
Cured Properties	Nominal Value	Unit
Shore Hardness (Shore D)	80 to 85	
Lap Shear Strength <sup>4</sup>	8.27	MPa
Volume Resistivity	1.0E-4	ohms·cm
volume Resistivity	1.0L-4	Offilis Citi
NOTE NOTE	1.01-4	Offins Citi
·	Part B	Offins Citi
NOTE		Offins Ciff
NOTE  1.	Part B	Offins Citi

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

