

Ablebond 8350M

Epoxy; Epoxide
Henkel Ablestik

Message:

Ablebond 8350M is an Epoxy; Epoxide (Epoxy) material filled with silver. It is available in North America. Primary attribute of Ablebond 8350M: Conductive.
Typical applications include:
Adhesives/Tapes
Electrical/Electronic Applications

General Information			
Filler / Reinforcement	Silver		
Features	Electrically Conductive		
Uses	Adhesives		
	Bonding		
	Electrical Parts		
Forms	Pellets		
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	85.0	°C	ASTM E1356
CLTE - Flow	3.0E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	1.8	W/m/K	ASTM C177
Thermoset	Nominal Value	Unit	Test Method
Pot Life (25°C)	1400	min	
Shelf Life (-40°C)	52	wk	
Thermoset Mix Viscosity (25°C)	11000	cP	ASTM D2393
Demold Time (150°C)	10	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT