

ALPERFORM PC LD

Polycarbonate
ALBIS PLASTIC GmbH

Message:

ALPERFORM PC LD is a polycarbonate (PC) product. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region.

Features include:

- Comply with REACH standard
- ROHS certification

General Information			
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	28.0	cm³/10min	ISO 1133
Injection	Nominal Value	Unit	
Drying Temperature			
Dehumidification desiccant	100 - 120	°C	
Hot air dryer	100 - 120	°C	
Drying Time			
Dehumidification desiccant	4.0 - 12	hr	
Hot air dryer	2.0 - 3.0	hr	
Processing (Melt) Temp	270 - 310	°C	
Mold Temperature	80 - 110	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT