

Karina BLACK PVC COMPOUND CAK 65-48/1

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

RECLAIMED PVC COMPOUND RECOMMENDED FOR SOLES AND INJECTED ARTICLES FOR GENERAL PURPOSES (WHOSE TEMPERATURE OF USE DO NOT EXCEED 40C).

General Information			
Recycled Content	Yes		
Uses	Footwear		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25 to 1.35	g/cm ³	ASTM D792
Color	0.00OK		ME 12
Color a	-0.720 to 0.880		ME 12
Color b	-1.02 to 0.580		ME 12
Color L	25.1 to 26.7		ME 12
Abrasion Resistance	< 300	mm ³	DIN 53516
Tear Resistance	> 25.0	kN/m	DIN 53507
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	63 to 67		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 4.90	MPa	ASTM D638
Tensile Elongation (Yield)	> 200	%	ASTM D638

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

