

CALIBRE™ 302V-15

Polycarbonate Resin

Trinseo

Message:

CALIBRE™ 300V-15 Series polycarbonate resins offer exceptional impact resistance, heat distortion resistance, optical clarity and meets UL94 V-2 rating. The CALIBRE 300V series products are available in 2 additive packages: CALIBRE 302V: UV stabilizer. CALIBRE 303V: Mold release and UV stabilizer.

Govt. And Industry Standards:

CSA (Canadian Standards Association)

UL (Underwriters Laboratory, Inc.)

Applications:

Electronic components

Lighting

Storage media housings

General Information			
UL YellowCard	E54680-469965	E54680-469966	E206114-228278
Additive	UV Stabilizer		
Features	High Clarity		
	High Impact Resistance		
Uses	Electrical/Electronic Applications		
	Housings		
	Lighting Applications		
Agency Ratings	CSA Unspecified Rating		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density			
--	1.20	g/cm ³	ISO 1183/B
--	1200	kg/m ³	ISO 1183 ¹
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15	g/10 min	ISO 1133
Melt volume-flow rate (300°C/1.2 kg)	12.0	cm ³ /10min	ISO 1133 ²
Molding Shrinkage - Flow	0.50 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2/50, ISO 527-2 ³
Tensile Stress			
Yield	60.0	MPa	ISO 527-2/50, ISO 527-2 ⁴
Break	71.0	MPa	ISO 527-2/50
Tensile Strain			
Yield	6.0	%	ISO 527-2/50, ISO 527-2 ⁵
Break	150	%	ISO 527-2/50

Nominal strain at break	> 50	%	ISO 527-2 ⁶
Flexural Modulus ⁷	2400	MPa	ISO 178
Flexural Stress ⁸	97.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
23°C	25	kJ/m ²	ISO 179/1eA
-30°C	12.0	kJ/m ²	ISO 179/1eA ⁹
23°C	80.0	kJ/m ²	ISO 179/1eA ¹⁰
Charpy impact strength			ISO 179/1eU ¹¹
-30°C	No Break		
23°C	No Break		
Notched Izod Impact (23°C)	850	J/m	ISO 180/4A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Annealed	140	°C	ISO 75-2/B
0.45 MPa	144	°C	ISO 75-2 ¹²
1.8 MPa, Unannealed	121	°C	ISO 75-2/A
1.8 MPa, Annealed	137	°C	ISO 75-2/A
1.8 MPa	130	°C	ISO 75-2 ¹³
Vicat Softening Temperature			
--	145	°C	ISO 306/B50
50°C/h, B (50N)	148	°C	ISO 306 ¹⁴
Ball Indentation Temperature	125	°C	IEC 60335-1
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2 ¹⁵
Electrical	Nominal Value	Unit	Test Method
Volume resistivity	> 1.0E+13	ohms·m	IEC 60093 ¹⁶
Electric strength	17	kV/mm	IEC 60243-1 ¹⁷
Relative Permittivity			IEC 60250 ¹⁸
100 Hz	3.00		
1 MHz	3.00		
Dissipation Factor			IEC 60250 ¹⁹
100 Hz	1.0E-3		
1 MHz	2.0E-3		
Comparative Tracking Index (2.00 mm, Solution A)	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating ²⁰			UL 94
1.60 mm	V-2		
3.20 mm	V-2		
Burning Behav. at 1.6mm nom. thickn. (1.60 mm, UL)	V-2		ISO 1210 ²¹
Burning Behav. at thickness h (3.20 mm, UL)	V-2		ISO 1210 ²²

Oxygen index	26	%	ISO 4589-2 ²³
NOTE			
1.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
2.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
3.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
4.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
5.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
6.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
7.	2.0 mm/min		
8.	2.0 mm/min		
9.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
10.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
11.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
12.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
13.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
14.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
15.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
16.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
17.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		
18.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.		

19.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
20.	This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.
21.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
22.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
23.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

