

MIRASON™ NEO23H

Low Density Polyethylene

Mitsui Chemicals, Inc.

Message:

MIRASON™ NEO23H is a Low Density Polyethylene material. It is available in Asia Pacific. Primary attribute of MIRASON™ NEO23H: High Strength.

Typical applications include:

Film

Packaging

General Information			
Features	High Strength		
Uses	Film		
	Packaging		
Appearance	Clear/Transparent		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.921	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.3	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	53		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	14.7	MPa	ASTM D638
Tensile Elongation (Break)	600	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	94.0	°C	ASTM D1525
Melting Temperature	109	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT